SCHOMBURG GmbH & Co. KG

Aquafinstrasse 2 - 8 D-32760 Detmold (Germany) phone +49-5231-953-00

fax +49-5231-953-108 email export@schomburg.de

www.schomburg.com





Technical Data Sheet

BLANKOL-0

Art.-No. 4 06101

Solvent free release and impregnating oil

- no build-up, neutral odour, solvent free impregnating and release oil
- minimiert Quellen und Verspröden von Holzschalungen
- protects steel/iron manufacturing plants as well as steel formwork in general from the formation of rust - therefore preventing rust flecks in the concrete
- biodegradable in accordance with test certificate

Areas of application:

BLANKOLO is especially for use in pre-cast concrete manufacturing plants and building yards. BLANKOLO is suitable for preservation when out of action for a short period, for impregnating base boards whilst also using as a concrete release agent. The areas of application include large formwork sections, timber formwork, moulds/templates and base boards. Steel formwork may be preheated up to +60°C.

Technical Data:

Colour: yellowish
Consistency: liquid

Density: 0.89 g/cm^3

Consumption: Dependent on the absorption

of the substrate $15-50 \text{ g/m}^2$

Storage: cool and dry, 24 month in the original

unopenend container. Use opened

containers promptly.

Packaging: 1000 | IBCs

210 | drums 25 | kegs

Product application:

BLANKOLO is to be applied evenly and as thin as possible onto the clean and dry mould.

After spraying, drain off with a mineral oil resistant squeegee if necessary.

Important Advice:

- Suitability tests should be carried out prior to usage.
- Avoid puddles!
- Excessive coating can lead to incrustations and build-ups.
- Heated moulds up to maximum + 60 °C!
- BLANKOL-O cannot be diluted with water.
- Excess material can be removed with a foam rubber squeegee resistant to mineral oils.

Please observe a valid EU safety data sheet! **GISCODE: BTM 10**

This technical data sheet is a translation from German and does not consider local building codes or legal requirements. It shall be used as general reference for the product. Legally binding is only the German technical data sheet or the latest Data sheet from one of our foreign subsidiaries inside their sales territory.

'1 TB/CoS/TM 35/17